

SECTION 19: WIRE TABLES*

TABLE 62

Bare Copper Wire, A.W.G. (20° C. = 68° F.)

A.W.G. No.	Dia- meter Mils	Area Circular Mils	Area Square Inches	Ohms per 1000 Feet	Ohms per Pound	Feet per Pound	Pounds per 1000 Feet
0000	460	211 600	.166 2	.04901	.000 076 52	1 561	640.5
000	410	167 800	.131 8	.06180	.000 121 7	1 968	507.9
00	364.8	133 100	.104 5	.07793	.000 193 5	2 482	402.8
0	324.9	105 500	.082 89	.09827	.000 307 6	3 130	319.5
1	289.3	83 700	.065 73	.1239	.000 489 1	3 947	253.3
2	257.6	66 400	.052 13	.1563	.000 777 8	4 977	200.9
3	229.4	52 600	.041 34	.1970	.001 237	6 276	159.3
4	204.3	41 700	.032 78	.2485	.001 966	7 914	126.4
5	181.9	33 100	.026 00	.3133	.003 127	9 980	100.2
6	162.0	26 250	.020 62	.3951	.004 972	12 58	79.46
7	144.3	20 820	.016 35	.4882	.007 905	15.87	63.02
8	128.5	16 510	.012 97	.6282	.012 57	20.01	49.98
9	114.4	13 090	.010 28	.7921	.019 99	25.23	39.63
10	101.9	10 380	.008 155	.9989	.031 78	31.82	31.43
11	90.7	8 230	.006 467	1.260	.050 53	40.12	24.92
12	80.8	6 530	.005 129	1.588	.080 35	50.59	19.77
13	72.0	5 180	.004 067	2.003	.1278	63.80	15.68
14	64.1	4 110	.003 225	2.525	.2032	80.44	12.43
15	57.1	3 257	.002 358	3.184	.3230	101.4	9.858
16	50.8	2 583	.002 028	4.016	.5136	127.9	7.818
17	45.3	2 048	.001 609	5.064	.8167	161.3	6.200
18	40.3	1 624	.001 276	6.385	1.299	203.4	4.917
19	35.89	1 288	.001 012	8.051	2.065	256.5	3.899
20	31.96	1 022	.000 802 3	10.15	3.283	323.4	3.092
21	28.46	810	.000 636 3	12.80	5.221	407.8	2.452
22	25.35	642	.000 504 6	16.14	8.301	514.2	1.945
23	22.57	509	.000 400 2	20.36	13.20	648.4	1.542
24	20.10	404	.000 317 3	25.67	20.99	817.7	1.223
25	17.90	320.4	.000 251 7	32.37	33.37	1 031.0	0.9699
26	15.94	254.1	.000 199 6	40.81	53.06	1 300	0.7692
27	14.20	201.5	.000 158 3	51.47	84.37	1 639	0.6100
28	12.64	159.8	.000 125 5	64.90	134.2	2 067	0.4837
29	11.26	126.7	.000 099 53	81.83	213.3	2 607	0.3836
30	10.03	100.5	.000 078 94	103.2	339.2	3 287	0.3042
31	8.928	79.70	.000 062 60	130.1	539.3	4 145	0.2413
32	7.950	63.21	.000 049 64	164.1	857.6	5 227	0.1913
33	7.080	50.13	.000 039 37	206.9	1 364.0	6 591	0.1517
34	6.305	39.75	.000 031 22	260.9	2 168	8 310	0.1203
35	5.615	31.52	.000 024 76	329.0	3 448	10 480	0.095 42
36	5.000	25.00	.000 019 64	414.8	5 482	13 210	0.075 61
37	4.453	19.83	.000 015 57	532.1	8 717	16 660	0.060 01
38	3.965	15.72	.000 012 35	659.6	13 860	21 010	0.047 50
39	3.531	12.47	.000 009 793	831.8	22 040	26 500	0.037 74
40	3.145	9.888	.000 007 766	1 049.0	35 040	33 410	0.029 93
41	2.75	7.5625	.000 005 940	1 370	59 990	43 700	.022 09
42	2.50	6.2500	.000 004 909	1 660	87 700	52 800	.018 92
43	2.25	5.0625	.000 003 976	2 050	133 700	65 300	.015 32
44	2.00	4.0000	.000 003 142	2 600	214 000	82 600	.012 11
45	1.75	3.0625	.000 002 405	3 390	356 200	107 900	.009 27
46	1.50	2.2500	.000 001 767	4 610	676 800	146 800	.006 81

Table 63
Bare Copper Wire S.W.G. (60° F)

S.W.G. No.	Dia- meter Mils	Area Circular Mils	Area Square Inches	Ohms per 1000 Feet	Ohms per Pound	Feet per Pound	Pounds per 1000 Feet
4/0	400	160 000	.125 66	.06368	.000 131 46	2 064	484.4
3/0	372	138 400	.108 69	.0736	.000 175 74	2 390	418.9
2/0	348	121 100	.095 11	.0841	.000 229 5	2 730	366.7
1/0	324	105 000	.082 45	.0971	.000 305 4	3 147	317.8
1	300	90 000	.070 69	.1132	.000 415 5	3 670	272.5
2	276	76 180	.059 83	.1338	.000 580 0	4 338	230.6
3	252	63 500	.049 88	.1605	.000 834 5	5 200	192.3
4	232	53 820	.042 27	.1893	.001 161 7	6 139	162.9
5	212	44 940	.035 30	.2267	.001 666 1	7 348	136.1
6	192	36 860	.028 95	.2764	.002 476	8 961	111.6
7	176	30 980	.024 33	.3289	.003 507	10 66	93.8
8	160	25 600	.020 11	.3980	.005 135	12 90	77.5
9	144	20 740	.016 286	.4914	.007 827	15.93	62.78
10	128	16 380	.012 868	.6219	.012 537	20.16	49.61
11	116	13 460	.010 568	.7570	.018 587	24.55	40.74
12	104	10 820	.008 495	.942	.028 77	30.54	32.75
13	92	8 464	.006 648	1.204	.046 98	39.01	25.63
14	80	6 400	.005 027	1.592	.082 16	51.60	19.38
15	72	5 184	.004 072	1.966	.125 23	63.73	15.69
16	64	4 096	.003 217	2.488	.2006	80.65	12.40
17	56	3 136	.002 463	3.249	.3422	105.4	9.49
18	48	2 304	.001 809 6	4.422	.6340	143.3	6.98
19	40	1 600	.001 256 6	6.368	1 3146	206.4	4.844
20	36	1 296	.001 017 9	7.860	2 004	254.8	3.924
21	32	1 024	.000 804 2	9.950	3 209	322.6	3.100
22	28	784	.000 615 8	12.997	5 475	421.2	2.374
23	24	576	.000 452 4	17.69	10 144	573.4	1.744
24	22	484	.000 380 1	21.05	14 366	682.6	1.465
25	20	400	.000 314 2	25.47	21.03	825.8	1.211
26	18	324	.000 254 5	31.45	32.06	1 019	0.981
27	16.4	269	.000 211 2	37.88	46.52	1 229	0.814
28	14.8	219	.000 172 03	46.52	70.14	1 508	0.6632
29	13.6	185	.000 145 27	55.09	98.37	1 786	0.5600
30	12.4	153.8	.000 120 76	66.27	142.35	2 148	0.4655
31	11.6	134.6	.000 105 68	75.7	185.87	2 455	0.4074
32	10.8	116.6	.000 091 61	87.4	247.4	2 832	0.3531
33	10.0	100.0	.000 078 54	101.9	336.5	3 302	0.3028
34	9.2	84.64	.000 066 48	120.4	469.8	3 901	0.2563
35	8.4	70.56	.000 055 42	144.4	676.0	4 682	0.2136
36	7.6	57.76	.000 045 36	176.4	1 008.7	5 718	0.1749
37	6.8	46.24	.000 036 32	220.4	1 574	7 143	0.1400
38	6.0	36.00	.000 028 27	283.0	2 586	9 174	0.1090
39	5.2	27.04	.000 021 24	376.8	4 603	12 210	0.0819
40	4.8	23.04	.000 018 096	442.2	6 340	14 330	0.0698
41	4.4	19.36	.000 015 205	526.3	8 979	17 060	0.058 62
42	4.0	16.00	.000 012 566	636.8	13 146	20 640	.048 44
43	3.6	12.96	.000 010 179	786.3	20 400	25 480	.039 24
44	3.2	9.734	.000 008 042	995.0	32 090	32 260	.031 00
45	2.8	7.840	.000 006 158	1 299.7	54 750	42 120	.023 74
46	2.4	5.760	.000 004 524	1 769	101 440	57 340	.017 44
47	2.0	4.000	.000 003 142	2 547	210 300	82 580	.012 11
48	1.6	2.560	.000 002 011	3 980	513 500	129 000	.007 75
49	1.2	1.440	.000 001 131	7 077	1 623 000	229 400	.004 36
50	1.0	1.000	.000 000 785 4	10 190	3 365 000	303 000	.003 03

TABLE 64
TURNS PER INCH AND INSULATED WIRE DIAMETER A.W.G.
COPPER WIRE

AWG No.	Diameter (mils)		Turns per inch (exact winding)						D.S.C.
	*Enam.	D.C.C.	Bare	Enam.	S.C.C.	D.C.C.	S.S.C.		
8	130.6	142.5	7.78	7.65	7.32	7.01	—	—	
9	116.5	126.4	8.74	8.58	8.23	7.91	—	—	
10	104.0	112.9	9.81	9.61	9.26	8.85	—	—	
11	92.7	100.2	11.02	10.7	10.4	9.98	—	—	
12	82.8	90.3	12.37	12.0	11.6	11.07	—	—	
13	74.0	81.5	13.89	13.5	12.9	12.27	—	—	
14	66.1	73.6	15.60	15.1	14.4	13.59	—	—	
15	59.1	66.6	17.52	16.9	16.1	15.0	—	—	
16	52.8	60.3	19.68	18.9	17.9	16.5	18.9	18.2	
17	47.1	54.8	22.1	21.2	19.8	18.2	21.1	20.2	
18	42.1	49.8	24.8	23.7	22.0	20.0	23.6	22.5	
19	37.7	45.4	27.8	26.5	24.4	22.0	26.3	25.0	
20	33.8	41.5	31.3	29.5	27.0	24.1	29.4	27.7	
21	30.2	38.0	35.1	33.1	29.8	26.3	32.7	30.7	
22	27.0	33.8	39.4	37.0	33.5	29.5	36.6	34.1	
23	24.1	31.1	44.3	41.4	36.9	32.1	40.6	37.5	
24	21.5	28.6	49.7	46.5	40.6	34.9	45.2	41.4	
25	19.2	26.4	55.8	52.0	44.6	37.8	50.0	45.6	
26	17.1	24.4	62.7	58.4	49.0	40.9	55.8	50.0	
27	15.3	22.7	70.4	65.3	53.4	44.0	61.7	54.9	
28	13.6	21.1	82.8	73.5	58.4	47.3	68.4	60.2	
29	12.2	19.8	88.8	81.9	63.2	50.5	75.1	65.3	
30	10.8	18.5	99.7	92.5	68.9	54.0	83.3	71.4	
31	9.7	17.4	112.0	103	74.6	57.4	91.7	77.5	
32	8.7	16.5	125.8	114	80.0	60.6	100	83.3	
33	7.7	15.6	141.2	129	86.2	64.1	109	90.0	
34	6.9	14.8	158.6	144	92.5	67.5	120	97.0	
35	6.2	14.1	178	161	99.9	70.9	131	104	
36	5.5	13.0	200	181	111	76.9	142	111	
37	4.9	12.5	224	204	117	80.0	153	117	
38	4.4	12.0	252	227	125	83.3	166	125	
39	3.9	11.5	283	256	133	86.9	181	133	
40	3.5	11.1	318	285	140	90.0	196	140	
(41)	3.05	—	363	327	—	—	—	—	
(42)	2.64	—	400	378	—	—	—	—	
(43)	2.37	—	444	421	—	—	—	—	
(44)	2.12	—	500	471	—	—	—	—	
(45)	1.91	—	571	523	—	—	—	—	
(46)	1.72	—	666	581	—	—	—	—	

*Nominal Value. Actual dimensions vary slightly.

TABLE 65
TURNS PER INCH AND INSULATED WIRE DIAMETER, S.W.G.
COPPER WIRE

SWG No.	Diameter (mils)		Turns per inch (exact winding)						D.S.C.
	*Enam.	D.C.C.	Bare	Enam.	S.C.C.	D.C.C.	S.S.C.		
10	132	142	7.81	7.63	7.35	7.04	—	—	
11	120	130	8.62	8.33	8.07	7.69	—	—	
12	108	118	9.62	9.26	8.93	8.48	—	—	
13	96	106	10.87	10.42	10.00	9.43	—	—	
14	84	94	12.50	11.90	11.36	10.64	—	—	
15	75.5	84	13.89	13.25	12.66	11.90	—	—	
16	67.5	76	15.63	14.81	14.08	13.16	14.93	14.71	
17	59	68	17.86	16.95	15.87	14.71	16.95	16.67	
18	50.7	59	20.83	19.72	18.18	16.95	20.00	19.61	
19	42.6	51	25.00	23.47	21.28	19.61	23.81	23.26	
20	38.5	47	27.78	25.97	23.81	21.28	26.32	25.64	
21	34.3	43	31.25	29.15	26.32	23.26	29.41	28.57	
22	30.0	39	35.71	33.33	29.41	25.64	33.33	32.26	
23	25.7	34	41.67	38.91	34.48	29.41	38.46	37.04	
24	23.6	32	45.45	42.37	37.04	31.25	42.55	40.00	
25	21.5	30	50.00	46.51	40.00	33.33	46.51	43.48	
26	19.4	28	55.56	51.55	43.48	35.71	51.81	48.78	
27	17.7	26.4	60.98	56.50	46.73	37.88	56.50	52.91	
28	16.0	24.8	67.57	62.50	50.51	40.32	62.11	57.80	
29	14.8	23.6	73.53	67.57	53.76	42.37	67.11	62.11	
30	13.4	22.4	80.65	74.63	57.47	44.64	72.99	67.11	
31	12.6	21.6	86.21	79.37	60.24	46.30	77.52	70.92	
32	11.7	20.8	92.59	85.47	63.29	48.08	82.64	75.19	
33	10.9	20.0	100.00	91.74	66.67	50.00	88.50	80.00	
34	10.0	19.2	108.7	100.0	70.42	52.08	95.24	85.47	
35	9.1	17.4	119.0	109.9	80.65	57.47	103.1	91.74	
36	8.3	16.6	131.6	120.5	86.21	60.24	112.4	99.01	
37	7.4	15.8	147.1	135.1	99.21	63.29	123.5	107.5	
38	6.6	15.0	166.7	151.5	100.0	66.67	137.0	117.6	
39	5.7	14.2	192.3	175.4	108.7	70.42	153.8	129.9	
40	5.3	13.8	208.3	188.7	113.6	72.46	163.9	137.0	
41	4.8	—	227.3	208.3	—	—	178.6	151.5	
42	4.4	—	250.0	227.3	—	—	192.3	161.3	
43	3.9	—	277.8	256.4	—	—	208.3	172.4	
44	3.5	—	312.5	285.7	—	—	227.3	185.2	
45	3.1	—	357.1	322.6	—	—	250.0	200.0	
46	2.65	—	416.7	377.4	—	—	277.8	217.4	
47	2.25	—	500.0	444.4	—	—	312.5	238.1	
48	—	—	—	—	—	—	—	—	

*Nominal Value. Actual dimensions vary slightly.

TABLE 66

MULTI-LAYER COIL WINDING AND WEIGHT OF INSULATED WIRE,
A.W.G.

COPPER WIRE

AWG No.	Enamelled			D.C.C.			Weight—lbs. per 1000ft.		
	Turns per square inch *	Ohms per cubic inch *	Turns per square inch insulated	Turns per square inch *	Ohms per cubic inch *	Enam.	D.C.C.	D.S.C.	
8	57	.003 15	Paper insulated each layer. 20% allowance for waste space at ends of layers.	48	.002 65	50.55	51.15		
9	72	.004 75		59	.003 88	40.15	40.60		
10	90	.007 48		76	.006 31	31.80	32.18		
11	113	.011 83		93	.009 74	25.25	25.60		
12	141	.018 78		114	.015 19	20.05	20.40		
13	177	.029 5		140	.023 3	15.90	16.20		
14	221	.046 4		171	.035 9	12.60	12.91		
15	277	.073 4		208	.055 1	10.00	10.33		
16	348	.116 2		260	.086 9	7.930	8.210	7.955	
17	437	.184 0		316	.133 1	6.275	6.540	6.315	
18	548	.291 0		378	.200 8	4.980	5.235	5.015	
19	681	.456 0		455	.304 8	3.955	4.220	3.990	
20	852	.720 0		545	.460 5	3.135	3.373	3.173	
21	1 065	1.134	Paper insulated each layer. 20% allowance for waste space at ends of layers.	650	.692 0	2.490	2.685	2.520	
22	1 340	1.800		865	1.162	1.970	2.168	2.006	
23	1 665	2.820		1 030	1.774	1.565	1.727	1.593	
24	2 100	4.488		1 420	2.596	1.245	1.398	1.272	
25	2 630	7.080		1 750	3.822	.988	1.129	1.018	
26	3 320	11.27	4 mil. paper	2 030	5.740	.7845	.9140	.8100	
27	4 145	17.75		2 620	8.330	.6220	.7560	.6450	
28	5 250	28.34		3 250	12.15	.4940	.6075	.5140	
29	6 510	44.32		3 920	17.30	.3915	.4890	.4130	
30	8 175	70.15		4 780	25.15	.3105	.3955	.3330	
31	10 200	110.4	2 mil. paper	3 330	36.05	.2465	.3257	.2678	
32	12 650	127.6		8 250	50.76	.1960	.2700	.2170	
33	16 200	279.0		10 600	71.30	.1550	.2270	.1750	
34	19 950	433.2		12 400	99.77	.1230	.1928	.1412	
35	25 000	684.5		15 200	138.7	.0980	.1600	.1130	
36	31 700	1 094	1 mil. paper	5 550	191.6	.0776	.1361	.0920	
37	39 600	1 723		26 300	263	.0616	.1204	.0740	
38	49 100	2 693		32 000	357	.0488	.1049	.0623	
39	62 600	4 332		40 000	480	.0387	.0937	.0504	
40	77 600	6 770		48 400	650	.0307	.0838	.0429	

Paper insulated each layer.
20% allowance for waste space at ends of layers.

4 mil. paper

2 mil. paper

1 mil. paper

*For exact winding with no allowance for space factor.

TABLE 67

MULTI-LAYER COIL WINDING AND WEIGHT OF INSULATED WIRE,
S.W.G.

COPPER WIRE

SWG No.	Turns per square inch *	Ohms per cubic inch *	Turns per square inch insulated	Turns per square inch *	Ohms per cubic inch *	Enam.	D.C.C.	D.S.C.
10	58.22	.002 95	Paper insulated each layer. 20% allowance for waste space at ends of layers.	49.56	.00256	47.77	50.77	
11	69.39	.004 37		59.14	.003 73	44.40	41.83	
12	85.75	.006 73		71.91	.005 65	33.04	33.71	
13	108.6	.010 9		88.92	.008 93	25.89	26.50	
14	141.6	.018 9		113.2	.015 0	19.60	20.12	
15	175.6	.028 7		141.6	.023 4	15.87	16.36	
16	219.3	.045 6		173.2	.035 8	12.56	12.67	12.56
17	287.3	.077 6		216.4	.058 5	9.607	10.03	9.640
18	388.9	.143 1		287.3	.105 5	7.060	7.43	7.093
19	550.8	.290		384.6	.204	4.910	5.262	4.945
20	674.4	.440	452.8	.296	3.987	4.267	4.011	
21	849.7	.705	541.0	.448	3.152	3.409	3.181	
22	1 109	1.200	657.4	.710	2.419	2.649	2.446	
23	1 513	2.23	864.9	1.26	1.779	1.918	1.807	
24	1 789	3.14	1 220	1.71	1.498	1.667	1.305	
25	2 162	4.58	1 460	2.35	1.241	1.392	1.247	
26	2 663	6.95	1 760	3.33	1.008	1.152	1.013	
27	3 192	10.05	2 080	4.51	.836	.977	.844	
28	3 906	15.18	2 500	6.28	.683	.811	.689	
29	4 570	20.9	2 870	8.23	.578	.699	.582	
30	5 565	30.7	3 430	10.98	.478	.604	.486	
31	6 304	39.8	3 840	13.45	.419	.524	.428	
32	7 310	53.1	4 360	16.83	.364	.467	.371	
33	8 409	71.2	5 680	21.15	.313	.412	.329	
34	10 000	100.5	6 670	27.3	.264	.328	.271	
35	12 080	145	7 920	39.3	.221	.317	.288	
36	14 520	212	9 360	53.1	.181	.238	.188	
37	18 220	336	11 400	73.5	.146	.207	.151	
38	22 950	544	14 100	104.5	.114	.169	.119	
39	30 770	965	20 900	155.0	.0854	.138	.0868	
40	35 610	1 310	24 000	193.5	.0726	.123	.0791	
41	43 390	1 905	28 800		.0608		.0677	
42	51 620	2 740	33 700		.0505		.0571	
43	65 740	4 300	41 800		.0408		.0473	
44	81 620	6 760	50 800		.0324		.0386	
45	104 300	11 250			.0249		.0309	
46	142 100	21 000			.0182		.0231	
47	197 100	41 700			.0126		.0172	
48								

Paper insulated each layer.
20% allowance for waste space at ends of layers.

4 mil. paper

2 mil. paper

1 mil. paper

*For exact winding with no allowance for space factor.

TABLE 68

RESISTANCE WIRE TABLE, A.W.G.

20° C. (68° F.)

AWG No.	Dia. mils.	Advance Wire			Nichrome Wire**			
		Ohms per 1,000 feet	Lbs. per 1,000 feet	Feet per Ohm	Current Milli Amps *	Ohms per 1,000 feet	Lbs. per 1,000 feet	Current Milli Amps†
8	128	17.9	50	55.9	—	40.8	45	—
9	114	22.6	39	44.2	—	51.9	36	—
10	102	28.0	32	35.7	—	64.9	29	—
11	91	35.5	25	28.2	—	81.5	23	—
12	81	44.8	20	22.3	—	102	18	—
13	72	56.7	15.7	17.6	—	130	14	—
14	64	71.7	12.4	13.9	—	164	11	—
15	57	90.4	9.8	11.1	—	207	9.2	—
16	51	113	7.8	8.85	—	259	7.2	—
17	45	145	6.2	6.90	—	333	5.6	—
18	40	184	4.9	5.44	800	421	4.42	—
19	36	226	3.9	4.43	650	520	3.58	—
20	32	287	3.1	3.48	522	659	2.83	—
21	28.5	362	2.5	2.76	420	831	2.24	—
22	25.3	460	1.9	2.17	335	1 055	1.77	—
23	22.6	575	1.5	1.74	273	1 321	1.41	—
24	20.1	728	1.2	1.37	220	1 670	1.12	460
25	17.9	919	.97	1.09	178	2 106	.89	390
26	15.9	1 162	.77	.861	144	2 669	.70	330
27	14.2	1 455	.61	.687	117	3 347	.56	278
28	12.6	1 850	.48	.541	95	4 251	.44	228
29	11.3	2 300	.38	.435	78	5 286	.35	196
30	10.0	2 940	.30	.340	63	6 750	.276	165
31	8.9	3 680	.24	.272	52	8 521	.199	158
32	8.0	4 600	.19	.217	43	10 546	.177	117
33	7.1	5 830	.15	.172	36	13 900	.139	97
34	6.3	7 400	.12	.135	29	17 006	.110	82
35	5.6	9 360	.095	.107	24	21 524	.087	69
36	5.0	11 760	.076	.085	20	27 000	.069	58
37	4.5	14 550	.060	.0687	17	33 333	.056	49
38	4.0	18 375	.047	.0544	14.5	42 187	.045	41
39	3.5	24 100	.038	.0415	12	55 102	.034	34
40	3.1	30 593	.028	.0327	10	70 239	.025	28
(41)	2.75	38 888	.0229	.0257	8.5	89 256	.0209	24
(42)	2.5	46 400	.0189	.0215	7.5	108 000	.0173	20.5
(43)	2.25	58 103	.0153	.0172	6.8	133 333	.0140	17.5
(44)	2.0	73 500	.0121	.0136	6.0	168 750	.0110	14.5
(45)	1.75	96 078	.0092	.0104	5.0	220 408	.0084	12.0
(46)	1.5	130 666	.0068	.0076	4.0	300 000	.0062	9.5

**Wire produced by some manufacturers differs considerably from the resistance values given.

*D.S.C. wound on spool.

†Bare wire on slab—well ventilated. Spacing between turns equal to wire diameter.

N.B.—To find current for Advance wire wound on slab, multiply Nichrome Current column by approx. 1.5.

TABLE 69

RESISTANCE WIRE TABLE, S.W.G.

SWG No.	Dia. mils.	Eureka Wire				Nichrome Wire**			
		Ohms per 1,000 feet	Lbs. per 1,000 feet	Feet per Ohm	Current Milli Amps*	Ohms per 1,000 feet	Lbs. per 1,000 feet	Current Milli Amps†	
10	128	17.4	49.7	57.5	—	40.8	45	—	
11	116	21.2	40.9	47.2	—	50.2	37.3	—	
12	104	26.4	32.9	37.9	—	62.4	29.5	—	
13	92	33.8	25.7	29.6	—	79.7	23.4	—	
14	80	44.6	19.5	22.4	—	105.4	17.7	—	
15	72	55.1	15.8	18.15	—	130	14.0	—	
16	64	69.8	12.5	14.33	—	164	11.3	—	
17	56	91.1	9.5	10.98	—	215	8.7	—	
18	48	123.9	7.0	8.07	—	292	6.4	—	
19	40	178.5	4.9	5.60	—	421	4.42	—	
20	36	220.4	3.9	4.53	650	520	3.58	—	
21	32	279.1	3.12	3.58	510	659	2.83	—	
22	28	364	2.38	2.75	390	861	2.17	—	
23	24	496	1.75	2.02	300	1 170	1.60	—	
24	22	590	1.47	1.70	250	1 390	1.33	—	
25	20	714	1.21	1.40	210	1 680	1.12	—	
26	18	882	0.99	1.134	170	2 080	.897	400	
27	16.4	1 062	.82	.942	140	2 510	.746	350	
28	14.8	1 305	.67	.766	117	3 080	.607	300	
29	13.6	1 545	.56	.647	101	3 650	.513	250	
30	12.4	1 858	.47	.538	85	4 390	.427	230	
31	11.6	2 123	.41	.471	75	5 010	.373	205	
32	10.8	2 450	.35	.408	66	5 780	.324	185	
33	10.0	2 857	.304	.350	57	6 750	.276	165	
34	9.2	3 376	.257	.296	49	7 970	.235	145	
35	8.4	4 049	.215	.247	41	9 560	.195	125	
36	7.6	4 947	.175	.202	35	11 690	.160	110	
37	6.8	6 179	.140	.1618	29	14 600	.128	91	
38	6.0	7 936	.109	.1260	23	18 700	.100	76	
39	5.2	10 565	.082	.0947	19	24 900	.075	62	
40	4.8	12 935	.070	.0807	16	29 200	.064	55	
41	4.4	14 756	.059	.0677	13	34 800	.0536	48	
42	4.0	17 855	.049	.0560	11	42 180	.0450	41	
43	3.6	22 045	.039	.0454	9.5	52 000	.0358	35	
44	3.2	27 888	.031	.0359	8.0	63 900	.0283	30	
45	2.8	36 216	.024	.0276	6.5	86 100	.0217	25	
46	2.4	49 588	.018	.0202	5.0	117 000	.0160	20	
47	2.0	71 428	.012	.0140	4.0	168 000	.0112	15	
48	1.6	111 333	.008	.0090	3.0	263 600	.0071	—	

**Wire produced by some manufacturers differs considerably from the resistance values given.

*D.S.C. wound on spool.

†Bare wire on slab—well ventilated. Spacing between turns equal to wire diameter.

N.B.—To find current for Eureka wire wound on slab, multiply Nichrome Current column by approx. 1.5.